




BORA




BORA Blanc 01




BORA Mastic 48




BORA Anthracite 38




BORA Sienne 29




BORA Taupe 95




BORA Perle 96




BORA Terre 107




BORA Chamois 111



BORA Bordeaux 04



BORA Aubergine 27



BORA Noir 10




BORA Crème 02




BORA Bergamotte 121




BORA Tilleul 103



BORA Kaki 148



BORA Emeraude 88



BORA Indigo 144

drapilux
By Sotexpro

DRAPILUX GmbH - Hofenstraße 3, 77694 Kehl - Deutschland

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected



BORA Or 94

This plain fabric with shiny backing will enhance comfort levels in the premises by providing optimal protection against light radiation.

Technical properties



Flame retardant



Thermal

Applications Roman blinds - Lining - Curtains

Composition 100% FR polyester

Weight 260 g/m² 767 g/ml Width 295 cm

Fabric direction Room high or standard direction Fitting ↔ cm ↓ cm

Maintenance advice      

Certifications OEKO-TEX STANDARD 100 (CQ 1006/1)

Minimum order 1 linear(s) meter(s)

Technical characteristics

| | | |
|-----------------|-------------------------------|-----------------|
| Flame retardant | M1 / B1 / IMO PASS | |
| Optical index | Light reflexion : | 51 % |
| | Light absorption : | 49 % |
| | Light transmission : | 0 % |
| Thermal index | Solar reflexion : | 50 % |
| | Solar absorption : | 50 % |
| | Solar transmission : | 0 % |
| | UV transmission : | 0 % |
| | Gtot : | Gt 41 % Fc 69 % |
| Resilience | Lightfastness (units Class/8) | 3 |