


BOREAL



BOREAL Turquoise 53




BOREAL Océan 91



BOREAL Acier 18




BOREAL Gris 97




BOREAL Blanc 01




BOREAL Crème 02




BOREAL Mastic 48



BOREAL Taupe 95




BOREAL Chocolat 70




BOREAL Noir 10




BOREAL Mousse 92




BOREAL Moutarde 47




BOREAL Cuivre 50




BOREAL Terracotta 65




BOREAL Orange 15



BOREAL Fuchsia 33




BOREAL Bordeaux 04



BOREAL Prune 84



BOREAL BPI 00



BOREAL BPI 00

drapilux
By Sotexpro


DRAPILUX GmbH - Hofenstraße 3, 77694 Kehl - Deutschland

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected


BOREAL



BOREAL cactus 36



BOREAL emeraude 88





BOREAL nuit 128



BOREAL Titanium 98



BOREAL Faience 149



BOREAL Indigo 144

This fabric comes in a range of several colours. It meets all styles and atmospheres.

Technical properties



Flame retardant



Thermal



Acoustic

Applications Roman blinds - Valences - Lining - Bed runners - Curtains

Composition 100% FR polyester

Weight 260 g/m² Width 290 cm

Fabric direction Room high or standard direction Fitting ↔ cm ↓ cm

Maintenance advice

Certifications OEKO-TEX STANDARD 100 (CQ 1006/1)

Minimum order 1 linear(s) meter(s)

Technical characteristics

Flame retardant	M1 / B1 / IMO PASS / UNI 8456 / 9174 Classe Uno
Acoustic	Noise reduction coefficient (NRC) : 0.88
	Weighted sound absorption coefficient (a _w) : 0.90
	Acoustic absorption class (a _w) : A
Optical index	Light reflexion : 3 %
	Light absorption : 97 %
	Light transmission : 0 %
Thermal index	Solar reflexion : 27 %
	Solar absorption : 73 %
	Solar transmission : 0 %
	UV transmission : 0 %
	Gtot : Gt 48 % Fc 81 %
Resilience	Lightfastness (units Class/8) 4
	Dimensional Stability (%)
	Warp 0
	Weft 0
	Breaking Elongation
	Warp 17
	Weft 27
	Breaking load (daN)
	Warp 87
	Weft 110



DRAPILUX GmbH - Hafenstraße 3, 77694 Kehl - Deutschland

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected