



BORNEO ENVERS BLANC




BORNEO ENVERS
BLANC CIEL 07




BORNEO ENVERS
BLANC MOUSSE 92




BORNEO ENVERS
BLANC KAKI 148




BORNEO ENVERS
BLANC INDIGO 144




BORNEO ENVERS
BLANC ROSE 129




BORNEO ENVERS
BLANC CHANVRE 72



BORNEO ENVERS
BLANC SAFRAN 49



BORNEO ENVERS
BLANC CORAIL 14




BORNEO ENVERS
BLANC BRUN 23

drapilux
By Sotexpro

DRAPILUX GmbH - Hafenstraße 3, 77694 Kehl - Deutschland

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected



BORNEO ENVERS BLANC EMERAUDE 88

Technical properties



Flame retardant



Thermal



Acoustic

Applications Roman blinds - Curtains

Composition 100% polyester

Weight 440 g/m² 1232 g/ml Width 280 cm

Fabric direction Room high or standard direction Fitting ↔ cm ↓ cm

Maintenance advice     

Certifications OEKO-TEX STANDARD 100 (CQ 1006/1)

Minimum order 1 linear(s) meter(s)

Technical characteristics

Flame retardant	M1 / B1 / IMO PASS / UNI 8456 / 9174 Classe Uno	
Acoustic	Noise reduction coefficient (NRC) :	0.89
	Weighted sound absorption coefficient (a _w) :	0.90
	Acoustic absorption class (a _w) :	A
Optical index	Light reflexion :	60 %
	Light absorption :	40 %
	Light transmission :	0 %
Thermal index	Solar reflexion :	56 %
	Solar absorption :	44 %
	Solar transmission :	0 %
	UV transmission :	0 %
	Gtot :	Gt 39 % Fc 65 %
Resilience	Lightfastness (units Class/8)	6
	Dimentional Stability (%)	
	Warp	-0.5
	Weft	0
	Breaking Elongation	
	Warp	31
	Weft	0
	Breaking load (daN)	
	Warp	130
	Weft	250

drapilux
By Sotexpro

DRAPILUX GmbH - Hafenstraße 3, 77694 Kehl - Deutschland

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected