


COLLEGE




COLLEGE Naval 17




COLLEGE Anis 62




COLLEGE Poussin 20




COLLEGE Ficelle 09




COLLEGE Nacre 04




COLLEGE Naturel 26




COLLEGE acier 18




COLLEGE Corail 14




COLLEGE Framboise 81




COLLEGE Marine 25




COLLEGE Gentiane 16




COLLEGE Turquoise 53




COLLEGE Vert 24




COLLEGE Mastic 48



COLLEGE Blanc 01



COLLEGE Souris 31



COLLEGE Moka 13



COLLEGE Mordoré 133



COLLEGE Paille 83




COLLEGE Pêche 52

drapilux
By Sotexpro


DRAPILUX GmbH - Hofenstraße 3, 77694 Kehl - Deutschland

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected


COLLEGE



COLLEGE Safran 49



COLLEGE Havane 44



COLLEGE Sanguine 05




COLLEGE Evêque 154



COLLEGE Bergamotte
121




COLLEGE Olive 61





COLLEGE Absinthe 132



COLLEGE Indigo 144



COLLEGE Titanium 98



COLLEGE Noir 10

This light-filtering fabric is available in a range of several colours, providing you with some great decoration possibilities.

Technical properties



Flame retardant



Thermal

Applications Roman blinds - Panel curtains - Curtains - Decorative frames

Composition 100% FR polyester

Weight 200 g/m² Width 140 cm / 280 cm

Fabric direction Room high or standard direction Fitting ↔ cm ↓ cm

Maintenance advice

Labels France Terre Textile (R016)

Certifications OEKO-TEX STANDARD 100 (CQ 1006/1)

Minimum order 1 linear(s) meter(s)

Technical characteristics

Flame retardant

M1 / EN13773 : 2003 Class 1 / B1 / IMO PASS / UNI 8456 / 9174 Classe Uno

Optical index

Light reflexion :	2 %
Light absorption :	93 %
Light transmission :	5 %

Thermal index

Solar reflexion :	28 %
Solar absorption :	53 %
Solar transmission :	19 %
UV transmission :	5 %
Gtot :	Gt 48 % Fc 81 %

Resilience

Lightfastness (units Class/8)	4
Dimensional Stability (%)	
Warp	-2.5
Weft	-0.5
Breaking Elongation	
Warp	23
Weft	24
Breaking load (daN)	
Warp	93
Weft	120