

COLLIOURE



COLLIOURE Olive 61



COLLIOURE Agrume 69



COLLIOURE Miel 17



COLLIOURE Mandarine
93



COLLIOURE Océan 91



COLLIOURE Pervenche
13



COLLIOURE Ardoise 08




COLLIOURE Glacier 43




COLLIOURE Souris 31




COLLIOURE Blanc 01




COLLIOURE Ivoire 02




COLLIOURE Naturel 26



COLLIOURE Brun 23



COLLIOURE Titanium 98




COLLIOURE Noir 12




COLLIOURE eucalyptus
117




COLLIOURE navy 120



COLLIOURE lin 11



COLLIOURE marine 25




COLLIOURE
Bergamotte 121

drapilux
By Sotexpro

DRAPILUX GmbH - Hafenstraße 3, 77694 Kehl - Deutschland

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected

COLLIOURE




COLLIOURE Absinthe
132




COLLIOURE Arctique 58



COLLIOURE Saumon
143




COLLIOURE Tomette 60




COLLIOURE Terre 107




COLLIOURE Aubergine
27




COLLIOURE Cacao 168



COLLIOURE Chataigne
55



COLLIOURE Pêche 52



COLLIOURE Chamois 111

This plain twill fabric comes in a range of several colours.

Technical properties



Flame retardant




Thermal

Applications Roman blinds - Panel curtains - Valences - Curtains - Cushions - Decorative frames

Composition 100% FR polyester

Weight 270 g/m² **Width** 140 cm / 280 cm

Fabric direction Room high or standard direction **Fitting** ↔ cm ↓ cm

Maintenance advice     

Labels France Terre Textile (R016)

Certifications OEKO-TEX STANDARD 100 (CQ 1006/1)

Minimum order 1 linear(s) meter(s)

Technical characteristics

Flame retardant	M1 / EN13773 : 2003 Class 1 / B1 / IMO PASS / UNI 8456 / 9174 Classe Uno	
Optical index	Light reflexion :	64 %
	Light absorption :	19 %
	Light transmission :	17 %
Thermal index	Solar reflexion :	64 %
	Solar absorption :	17 %
	Solar transmission :	19 %
	UV transmission :	3 %
	Gtot :	Gt 36 % Fc 61 %
Resilience	Lightfastness (units Class/8)	6
	Dimensional Stability (%)	
	Warp	-3
	Weft	-0.5
	Breaking Elongation	
	Warp	26
	Weft	28
	Breaking load (daN)	
Warp	100	
Weft	160	