

COLLIOURE



COLLIOURE Olive 61



COLLIOURE Agrume 69




COLLIOURE Miel 17




COLLIOURE Mandarine
93




COLLIOURE Océan 91




COLLIOURE Ardoise 08




COLLIOURE Glacier 43




COLLIOURE Souris 31




COLLIOURE Blanc 01



COLLIOURE Ivoire 02




COLLIOURE Naturel 26



COLLIOURE Brun 23



COLLIOURE Titanium 98




COLLIOURE Noir 12




COLLIOURE eucalyptus
117




COLLIOURE navy 120




COLLIOURE lin 11



COLLIOURE marine 25



COLLIOURE
Bergamotte 121



COLLIOURE Absinthe
132

drapilux
By Sotexpro

DRAPILUX GmbH - Hafenstraße 3, 77694 Kehl - Deutschland

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected


COLLIOURE



COLLIOURE Arctique 58




COLLIOURE Saumon
143




COLLIOURE Tomette 60



COLLIOURE Terre 107



COLLIOURE Aubergine
27




COLLIOURE Cacao 168



COLLIOURE Chataigne
55



COLLIOURE Chamois
111





COLLIOURE Pêche 52

drapilux
By Sotexpro

DRAPILUX GmbH - Hafenstraße 3, 77694 Kehl - Deutschland

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected



COLLIOURE Pervenche 13

This plain twill fabric comes in a range of several colours.

Technical properties



Flame retardant








Thermal

Applications Roman blinds - Panel curtains - Valences - Curtains - Cushions - Decorative frames

Composition 100% FR polyester

Weight 270 g/m² Width 140 cm / 280 cm

Fabric direction Room high or standard direction Fitting ↔ cm ↓ cm

Maintenance advice     

Labels France Terre Textile (R016)

Certifications OEKO-TEX STANDARD 100 (CQ 1006/1)

Minimum order 1 linear(s) meter(s)



Technical characteristics

Flame retardant

M1 / EN13773 : 2003 Class 1 / B1 / IMO PASS / UNI 8456 / 9174 Classe Uno

Optical index

Light reflexion : 33 %

Light absorption : 64 %

Light transmission : 3 %

Thermal index

Solar reflexion : 50 %

Solar absorption : 36 %

Solar transmission : 14 %

UV transmission : 1 %

Gtot : Gt 41 % Fc 69 %

Resilience

Lightfastness (units Class/8) 5

Dimensional Stability (%)

Warp -3

Weft -0.5

Breaking Elongation

Warp 26

Weft 28

Breaking load (daN)

Warp 100

Weft 160

drapilux
By Sotexpro

DRAPILUX GmbH - Hafenstraße 3, 77694 Kehl - Deutschland

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected