


CORTE




CORTE Eucalyptus 117




CORTE Naval 17



CORTE Orgeat 127




CORTE Miel 07




CORTE Noir 10




CORTE Anthracite 38




CORTE Mastic 48




CORTE Ivoire 02




CORTE Blanc 01




CORTE Souris 31



CORTE Taupe 95



CORTE Moka 13




CORTE Céladon 135



CORTE Faïence 149




CORTE Indigo 144



CORTE Absinthe 132



CORTE Ocre 03



CORTE Saumon 143



CORTE Hortensia 134




CORTE Cacao 168

drapilux
By Sotexpro

DRAPILUX GmbH - Hofenstraße 3, 77694 Kehl - Deutschland

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected



CORTE Opéra 04

This plain light-filtering fabric is available in several colours.

Technical properties



Flame retardant



Thermal








Acoustic

Applications Curtains - Cushions - Decorative frames - Roman blinds - Panel curtains
- Bedspreads - Valences - Seating - Bed runners

Composition 100% FR polyester

Weight 230 g/m² **Width** 140 cm / 280 cm

Fabric direction Room high or standard direction **Fitting** ↔ cm ↓ cm

Maintenance advice     

Labels France Terre Textile (R016)

Certifications OEKO-TEX STANDARD 100 (CQ 1006/1)

Minimum order 1 linear(s) meter(s)

Technical characteristics

Flame retardant	M1 / BS 5867 TYPE C / B1 / IMO PASS / UNI 8456 / 9174 Classe Uno
Acoustic	Noise reduction coefficient (NRC) : 0.90 Weighted sound absorption coefficient (a _w) : 0.85 Acoustic absorption class (a _w) : B
Optical index	Light reflexion : 3 % Light absorption : 97 % Light transmission : 0 %
Thermal index	Solar reflexion : 32 % Solar absorption : 56 % Solar transmission : 12 % UV transmission : 0 % Gtot : Gt 47 % Fc 79 %
Resilience	Lightfastness (units Class/8) 5 Pilling 4 Dimensional Stability (%) Warp -2 Weft -0.5 Martindale (Cycles) 25000 Breaking Elongation Warp 34 Weft 28 Breaking load (daN) Warp 130 Weft 90



DRAPILUX GmbH - Hafenstraße 3, 77694 Kehl - Deutschland

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected