




NOCTIS UNI




NOCTIS UNI Cassis 97



NOCTIS UNI Framboise
81




NOCTIS UNI Mandarine
15



NOCTIS UNI Abricot 93




NOCTIS UNI Agrume 69




NOCTIS UNI Emeraude
88



NOCTIS UNI Ardoise 87




NOCTIS UNI Lavande 89




NOCTIS UNI Océan 91



NOCTIS UNI Marine 25




NOCTIS UNI Crème 02




NOCTIS UNI Perle 96




NOCTIS UNI Mastic 48




NOCTIS UNI Lin 11



NOCTIS UNI Sienne 29



NOCTIS UNI Anthracite
38




NOCTIS UNI Graphite 77

drapilux
By Sotexpro

DRAPILUX GmbH - Hafenstraße 3, 77694 Kehl - Deutschland

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected



NOCTIS UNI Ecume 82

This plain fabric is a classic of our range, it is available in several colors. NOCTIS UNI is a flame retardant and antibacterial blackout fabric. It kills 99% of staphylococcus aureus and klebsiella pneumoniae bacteria (antibacterial action only on Noctis uni color gray flocked back). It does not release any biocidal product into the water when washing the fabric.

Technical properties



Flame retardant








Antibacterial

Applications Roman blinds - Roller blinds - Panel curtains - Lining - Curtains

Composition 100% polyester with gray flocked acrylic backing

Weight 330 g/m² **Width** 200 cm

Fabric direction Room high or standard direction **Fitting** ↔ cm ↓ cm

Maintenance advice     

Labels France Terre Textile (R016)

Minimum order 1 linear(s) meter(s)

Technical characteristics

| | |
|-----------------|---|
| Flame retardant | M1 / B1 / IMO PASS / UNI 8456 / 9174 Classe Uno |
| Acoustic | Noise reduction coefficient (NRC) : 0.28 |
| | Weighted sound absorption coefficient (a _w) : 0.20 |
| | Acoustic absorption class (a _w) : E |
| Antibacterial | Yes |
| Optical index | Light reflexion : 33 % |
| | Light absorption : 67 % |
| | Light transmission : 0 % |
| Thermal index | Solar reflexion : 34 % |
| | Solar absorption : 66 % |
| | Solar transmission : 0 % |
| | UV transmission : 0 % |
| | Gtot : Gt 46 % Fc 77 % |
| Resilience | Lightfastness (units Class/8) 6 |
| | Pilling 5 |
| | Dimensional Stability (%) |
| | Warp -0,5 |
| | Weft 0 |
| | Martindale (Cycles) 35000 |
| | Breaking Elongation |
| | Warp 20 |
| | Weft 24 |
| | Breaking load (daN) |
| Warp 53 | |
| Weft 63 | |

drapilux
By Sotexpro

DRAPILUX GmbH - Hafenstraße 3, 77694 Kehl - Deutschland

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected