



# OPALE 2




OPALE 2 Océan 91




OPALE 2 Cactus 09




OPALE 2 Mousse 92




OPALE 2 Agrume 69




OPALE 2 Terracotta 65




OPALE 2 Tomette 60




OPALE 2 Pivoine 57




OPALE 2 Rubis 08




OPALE 2 Aubergine 27




OPALE 2 Anthracite 38




OPALE 2 Souris 40




OPALE 2 Nacre 04




OPALE 2 Crème 02



OPALE 2 Sable 67




OPALE 2 Beige 63



OPALE 2 Brun 23



OPALE 2 Mastic 48



OPALE 2 Moka 12



OPALE 2 Marine 25



OPALE 2 Paille 06

**drapilux**  
By Sotexpro

DRAPILUX GmbH - Hafenstraße 3, 77694 Kehl - Deutschland

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected


# OPALE 2




OPALE 2 Titanium 98



OPALE 2 Noir 36



OPALE 2 emeraude 88



OPALE 2 taupe 95



OPALE 2 absinthe 132



OPALE 2 lin 11



# OPALE 2 Cyan 90

This plain fabric blocks out light very effectively and is available in a wide variety of colours.

## Technical properties



Flame retardant

**Applications** Roman blinds - Roller blinds - Panel curtains - Curtains

**Composition** 100% polyester with white flocked acrylic backing

**Weight** 290 g/m<sup>2</sup> **Width** 140 cm

**Fabric direction** Standard Direction **Fitting** ↔ cm ↓ cm

**Maintenance advice**     

**Minimum order** 1 linear(s) meter(s)



## Technical characteristics

Flame retardant	M1 / IMO PASS	
Optical index	Light reflexion :	72 %
	Light absorption :	28 %
	Light transmission :	0 %
Thermal index	Solar reflexion :	65 %
	Solar absorption :	35 %
	Solar transmission :	0 %
	UV transmission :	0 %
	Gtot :	Gt 35 % Fc 60 %
Resilience	Lightfastness (units Class/8)	5
	Breaking Elongation	
	Warp	35
	Weft	11