



BORA Perle 96

This plain fabric with shiny backing will enhance comfort levels in the premises by providing optimal protection against light radiation.

Technical properties



Thermal

Applications Roman blinds - Lining - Curtains

Composition 100% FR polyester

Weight 260 g/m² 767 g/ml Width 295 cm

Fabric direction Room high or standard direction Fitting ↔ cm ↓ cm

Maintenance advice      

Certifications OEKO-TEX STANDARD 100 (CQ 1006/1)

Minimum order 1 linear(s) meter(s)

Technical characteristics

Flame retardant	B1 / IMO PASS	
Optical index	Light reflexion :	51 %
	Light absorption :	49 %
	Light transmission :	0 %
Thermal index	Solar reflexion :	50 %
	Solar absorption :	50 %
	Solar transmission :	0 %
	UV transmission :	0 %
	Gtot :	Gt 41 % Fc 69 %
Resilience	Lightfastness (units Class/8)	3

drapilux
By Sotexpro

DRAPILUX GmbH - Hafenstraße 3, 77694 Kehl - Deutschland

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on supports selected