

# BOREAL Mastic 48

This plain fabric is available in a range of several colours, suitable for any style and mood.

## Technical properties



Flame retardant



Thermal




Acoustic

Applications Roman blinds - Valences - Lining - Bed runners - Curtains

Composition 100% FR polyester

Weight 260 g/m<sup>2</sup> Width 290 cm

Fabric direction Room high or standard direction Fitting ↔ cm ↓ cm

Maintenance advice     

Certifications OEKO-TEX STANDARD 100 (CQ 1006/1)

Minimum order 1 linear(s) meter(s)



## Technical characteristics

|                 |  |
|-----------------|--|
| Flame retardant | M1 / B1 / IMO PASS / UNI 8456 / 9174 Classe Uno  |
| Acoustic        | Noise reduction coefficient (NRC) : <b>0.88</b><br>Weighted sound absorption coefficient (a <sub>w</sub> ) : <b>0.90</b><br>Acoustic absorption class (a <sub>w</sub> ) : <b>A</b>   |
| Optical index   | Light reflexion : <b>55 %</b><br>Light absorption : <b>45 %</b><br>Light transmission : <b>0 %</b>   |
| Thermal index   | Solar reflexion : <b>53 %</b><br>Solar absorption : <b>47 %</b><br>Solar transmission : <b>0 %</b><br>UV transmission : <b>0 %</b><br>Gtot : <b>Gt 40 % Fc 67 %</b>  |
| Resilience      | Lightfastness (units Class/8) <b>6</b><br>Dimensional Stability (%)<br>Warp <b>0</b><br>Weft <b>0</b><br>Breaking Elongation<br>Warp <b>17</b><br>Weft <b>27</b><br>Breaking load (daN)<br>Warp <b>87</b><br>Weft <b>110</b> |

**drapilux**  
By Sotexpro

DRAPILUX GmbH - Hafenstraße 3, 77694 Kehl - Deutschland

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected