



# BORNEO ENVERS BLANC CHANVRE 72

## Technical properties



Flame retardant



Thermal



Acoustic

Applications Roman blinds - Curtains

Composition 100% polyester

Weight 440 g/m<sup>2</sup> 1232 g/ml Width 280 cm

Fabric direction Room high or standard direction Fitting ↔ cm ↓ cm

Maintenance advice      

Certifications OEKO-TEX STANDARD 100 (CQ 1006/1)

Minimum order 1 linear(s) meter(s)

## Technical characteristics

|                 |                                                           |                        |
|-----------------|-----------------------------------------------------------|------------------------|
| Flame retardant | M1 / B1 / IMO PASS / UNI 8456 / 9174 Classe Uno           |                        |
| Acoustic        | Noise reduction coefficient (NRC) :                       | <b>0.89</b>            |
|                 | Weighted sound absorption coefficient (a <sub>w</sub> ) : | <b>0.90</b>            |
|                 | Acoustic absorption class (a <sub>w</sub> ) :             | <b>A</b>               |
| Optical index   | Light reflexion :                                         | <b>60 %</b>            |
|                 | Light absorption :                                        | <b>40 %</b>            |
|                 | Light transmission :                                      | <b>0 %</b>             |
| Thermal index   | Solar reflexion :                                         | <b>56 %</b>            |
|                 | Solar absorption :                                        | <b>44 %</b>            |
|                 | Solar transmission :                                      | <b>0 %</b>             |
|                 | UV transmission :                                         | <b>0 %</b>             |
|                 | Gtot :                                                    | <b>Gt 39 % Fc 65 %</b> |
| Resilience      | Lightfastness (units Class/8)                             | <b>6</b>               |
|                 | Dimentional Stability (%)                                 |                        |
|                 | Warp                                                      | <b>-0.5</b>            |
|                 | Weft                                                      | <b>0</b>               |
|                 | Breaking Elongation                                       |                        |
|                 | Warp                                                      | <b>31</b>              |
|                 | Weft                                                      | <b>0</b>               |
|                 | Breaking load (daN)                                       |                        |
|                 | Warp                                                      | <b>130</b>             |
|                 | Weft                                                      | <b>250</b>             |

**drapilux**  
By Sotexpro

DRAPILUX GmbH - Hafenstraße 3, 77694 Kehl - Deutschland

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected