

LINOSA Anthracite 38

This plain, light-filtering fabric resembling linen is captivating and perfect for natural and warm décor.

Technical properties




Flame retardant

Applications Roman blinds - Panel curtains - Curtains - Cushions - Decorative frames

Composition 100% FR polyester

Weight 260 g/m² 0 g/ml **Width** 280 cm

Fabric direction Room high or standard direction **Fitting** ↔ cm ↓ cm

Maintenance advice     

Labels France Terre Textile (R016)

Certifications OEKO-TEX STANDARD 100 (CQ 1006/1)

Minimum order 1 linear(s) meter(s)



Technical characteristics

Flame retardant

M1 / B1 / IMO PASS / UNI 8456 / 9174 Classe Uno

Optical index

Light reflexion :	9 %
Light absorption :	86 %
Light transmission :	5 %

Thermal index

Solar reflexion :	36 %
Solar absorption :	45 %
Solar transmission :	19 %
UV transmission :	8 %
Gtot :	Gt 45 % Fc 77 %

Resilience

Lightfastness (units Class/8)	3
Pilling	1-2
Dimentional Stability (%)	
Warp	-2
Weft	-0.5
Martindale (Cycles)	30000
Breaking Elongation	
Warp	25
Weft	25
Breaking load (daN)	
Warp	140
Weft	100

drapilux
By Sotexpro

DRAPILUX GmbH - Hofenstraße 3, 77694 Kehl - Deutschland

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected