



**NATTE bpi 00**  
Printing support



**MURA MASTIC 48**  
Print pattern

## Printing support **NATTE bpi 00** Print pattern **MURA MASTIC 48**

This light-filtering fabric serves as a print medium.

### Technical properties



Flame retardant

**Applications** Roman blinds - Panel curtains - Bedspreads - Valences - Bed runners  
- Curtains - Cushions

**Composition** 100% FR polyester

**Weight** 230 g/m<sup>2</sup>

**Width** 280 cm

**Fabric direction** Room High Direction

**Fitting** ↔ 13.0 cm ↓ 13.0 cm

**Maintenance advice**     

**Label** France Terre Textile / OEKO-TEX STANDARD 100

**Minimum order** 25 linear(s) meter(s)



Visual not taking into account the printing medium, the final rendering may vary according to the chosen medium.

## Technical characteristics

|                           |                                     |                               |
|---------------------------|-------------------------------------|-------------------------------|
| Flame retardant           | M1 / IMO PASS                       |                               |
| Acoustic                  | Noise reduction coefficient (NRC) : | <b>0.90</b>                   |
| Optical index             | Light reflexion :                   | <b>5 %</b>                    |
|                           | Light absorption :                  | <b>94 %</b>                   |
|                           | Light transmission :                | <b>1 %</b>                    |
| Thermal index             | Solar reflexion :                   | <b>39 %</b>                   |
|                           | Solar absorption :                  | <b>48 %</b>                   |
|                           | Solar transmission :                | <b>13 %</b>                   |
|                           | UV transmission :                   | <b>0 %</b>                    |
|                           | Gtot :                              | <b>Gt 48 % Fc 69 %</b>        |
|                           | Resilience                          | Lightfastness (units Class/8) |
| Pilling                   |                                     | <b>5</b>                      |
| Dimensional Stability (%) |                                     |                               |
| Warp                      |                                     | <b>-2</b>                     |
| Weft                      |                                     | <b>-1</b>                     |
| Martindale (Cycles)       |                                     | <b>40000</b>                  |
| Breaking Elongation       |                                     |                               |
| Warp                      |                                     | <b>38</b>                     |
| Weft                      |                                     | <b>21</b>                     |
| Breaking load (daN)       |                                     |                               |
| Warp                      |                                     | <b>150</b>                    |
| Weft                      |                                     | <b>93</b>                     |

# Print pattern MURA



MURA NOIR 10



MURA GLACIER 43



MURA GRENAT 56



MURA OLIVE 61



MURA SAPHIR 106



MURA TERRE 107



MURA ROSE 129



MURA MINERAL 157



MURA DUNE 170



MURA ETAIN 180



MURA SAVANE 185