

SADYNA Ficelle 09

This plain, twill, light-filtering fabric is a classic. Perfect for simpler designs or to coordinate with our woven Jacquard patterns. Available in several colours.

Technical properties



Flame retardant



Thermal




Acoustic

Applications Roman blinds - Panel curtains - Valences - Bed runners - Curtains - Cushions - Decorative frames

Composition 100% FR polyester

Weight 320 g/m² **Width** 280 cm

Fabric direction Room high or standard direction **Fitting** ↔ cm ↓ cm

Maintenance advice     

Labels France Terre Textile (R016)

Certifications OEKO-TEX STANDARD 100 (CQ 1006/1)

Minimum order 1 linear(s) meter(s)

Technical characteristics

| | | |
|-----------------|---|------------------------|
| Flame retardant | M1 / B1 / IMO PASS | |
| Acoustic | Noise reduction coefficient (NRC) : | 0.88 |
| | Weighted sound absorption coefficient (a _w) : | 0.85 |
| | Acoustic absorption class (a _w) : | B |
| Optical index | Light reflexion : | 59 % |
| | Light absorption : | 28 % |
| | Light transmission : | 13 % |
| Thermal index | Solar reflexion : | 63 % |
| | Solar absorption : | 20 % |
| | Solar transmission : | 17 % |
| | UV transmission : | 4 % |
| | Gtot : | Gt 37 % Fc 62 % |
| Resilience | Lightfastness (units Class/8) | 6 |
| | Pilling | 2-3 |
| | Dimensional Stability (%) | |
| | Warp | -1.5 |
| | Weft | 0 |
| | Martindale (Cycles) | 20000 |
| | Breaking Elongation | |
| | Warp | 24 |
| | Weft | 22 |
| | Breaking load (daN) | |
| | Warp | 150 |
| Weft | 160 | |

drapilux
By Sotexpro

DRAPILUX GmbH - Hafenstraße 3, 77694 Kehl - Deutschland

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected