



SIENTO LITO Brousse 192

Light-filtering fabric made from recycled yarns. The proportion of recycled material and the manufacturing process of the yarn used to weave this quality can cause slight color variations between different batches of fabric.

Technical properties



Flame retardant



Recycled fabrics

Applications Roman blinds - Panel curtains - Curtains - Decorative frames

Composition 100% FR polyester including 90% recycled material

Weight 335 g/m² **Width** 280 cm

Fabric direction Room High Direction **Fitting** ↔ cm ↓ cm

Maintenance advice     

Labels France Terre Textile (R016)

Certifications OEKO-TEX STANDARD 100 Recyclé (CQ 1006/2)

Minimum order 1 linear(s) meter(s)

Technical characteristics

| | |
|-----------------|---|
| Flame retardant | M1 / B1 / IMO PASS / UNI 8456 / 9174 Classe Uno |
| Acoustic | Noise reduction coefficient (NRC) : 0.76 |
| | Weighted sound absorption coefficient (a _w) : 0.70 |
| | Acoustic absorption class (a _w) : C |
| Optical index | Light reflexion : 25 % |
| | Light absorption : 71 % |
| | Light transmission : 4 % |
| Thermal index | Solar reflexion : 41 % |
| | Solar absorption : 45 % |
| | Solar transmission : 14 % |
| | UV transmission : 2 % |
| | Gtot : Gt 44 % Fc 74 % |
| Resilience | Lightfastness (units Class/8) 5 |
| | Pilling 1 |
| | Dimensional Stability (%) |
| | Warp -1 |
| | Weft -0.5 |
| | Martindale (Cycles) 20000 |
| | Breaking Elongation |
| | Warp 49 |
| | Weft 34 |
| | Breaking load (daN) |
| | Warp 140 |
| Weft 79 | |

drapilux
By Sotexpro

DRAPILUX GmbH - Hofenstraße 3, 77694 Kehl - Deutschland

Non-contractual photos and colors - Indicative fitting - Fitting may vary depending on support selected